



VITON®

Manufacturer – West American Rubber (WARCO)

Gaskets meet the pressure ratings, drillings and dimensions of ANSI/ASME B16.2.1
ASTM D-2000/D-2240

Viton

Fluoroelastomer (FPM) rubber gasket

Media

- Most Common Chemicals
- Methane
- Chlorine Diluted Water (3%)
- Chlorinated Salt Brine



Specifications

Max. Temperature:	350	(° F)
Hardness Shore A	70 ± 5	
Tensile Strength ASTM F-152	1000	(PSI)

Availability

Full Face Ring 1/16" Thick 1/8" Thick 1/4" Thick

- Not recommended for use of MEK, steam and methanol.